

OVERHEAD CABLE

BACKGROUND OF THE INVENTION

5 1. Field of the Invention

 The present invention relates to an overhead cable designed to reduce the wind load.

 2. Description of the Related Art

 As an overhead cable of the related art, much
10 use is made of a steel-reinforced aluminum cable (ACSR) comprised of aluminum strands twisted together along the longitudinal direction around a steel core. As such an overhead cable designed to reduce the wind load of the overhead cable, as shown in Fig. 1, a cable obtaining by
15 twisting together aluminum strands 2 on a steel core 1, twisting together segment strands 3 along the longitudinal direction having a sector-form cross-section at the outermost layer, forming the corners of each segment strands 3 as arc surfaces, and preventing the
20 tangent of the arc of the intersection of the adjoining abutting surfaces of the segment strands 3 and the arc of the corners from passing through the center of the cable by setting the radius of curvature of the corner arc surface to a specific value and thereby reduce the wind
25 load is disclosed in Japanese Examined Patent Publication

(Kokoku) No. 57-46166.

As another overhead cable designed to reduce the wind load, an overhead cable obtained by setting the height of projections of spiral strands wound over an envelope of the outermost layer strands and the center
5 angles of the projections to specific values so as to reduce the wind load is disclosed in Japanese Examined Patent Publication (Kokoku) No. 5-6764.

As still another overhead cable designed to
10 reduce the wind load, an overhead cable obtained by making the surface of the outermost layer a wavy shape so as to reduce the wind load is disclosed in Japanese Examined Patent Publication (Kokoku) No. 7-34328.

These overhead cables above mentioned can give
15 effect of reducing the wind load.

Other type of overhead cable designed to reduce the wind load is disclosed in Japanese Unexamined Patent Publication (Kokai) No. 8-50814.

The overhead cable disclosed in the
20 publication, as shown in Fig. 2, is an overhead cable obtained by twisting together aluminum strands 2 on a steel core 1 along the longitudinal direction, twisting together segment strands 3 having a sector-form cross-section at the outermost layer and providing arc-shaped
25 grooves 4 at the front surface of the adjoining parts of

the segment strands.

This overhead cable has a circular sectional shape as its basic shape. It is formed with arc-shaped grooves in its front surface. The swirl created inside
5 the grooves causes the breakaway point of the flow to move to the downwind side of the overhead cable and thereby reduces a drag coefficient C_d .

The overhead cable disclosed in Japanese Unexamined Patent Publication (Kokai) No. 8-50814 gave
10 the effect of reducing the wind load when the diameter of the overhead cable was relatively large, but had the disadvantage that when the diameter of the overhead cable became small, the Reynolds number Re fell and, due to the relation of this lowered Reynolds number Re and the drag
15 coefficient C_d , the wind speed zone in which the drag coefficient C_d was lowered became remarkably high. For this reason, in an overhead cable having a small diameter, for example, a diameter of 25 mm or less, the design wind speed at which the drag coefficient C_d fell
20 became 60 to 70 m/s, which was not practical.

SUMMARY OF THE INVENTION

An object of the present invention is to provide an overhead cable designed to reduce the wind load acting
25 upon the overhead cable in a lower wind speed zone even

in a cable having a relatively small diameter.

According to the present invention, there is provided an overhead cable comprising: an outermost layer constituted by twisting together a plurality of segment
5 strands, and having a spiral groove along the longitudinal direction in the outer circumferential surface region of each boundary portion of adjoining segment strands, wherein in the contour of the cross-section of said outermost layer, each groove comprises an
10 arc-shaped curve having a predetermined radius R centered about a vertex of a regular polygon and each part between adjoining grooves comprises a straight line or a curve which is concave with respect to said straight line.

In the overhead cable of the present invention, the
15 fluctuation in pressure created at the cable surface depends upon the shape of the polygon and the fluctuations in pressure are made to occur at the vertexes of the polygon. As a result, the distribution of speed inside a laminar flow boundary layer collapsed to
20 cause turbulence at an early stage and therefore increase the speed in the bottom of the boundary layer.

For this reason, the breakaway point of the flow moves to the back flow side, a back flow zone of the cable is reduced, a negative pressure area generated
25 downwind of the cable is reduced, and therefore the drag

becomes smaller.

BRIEF DESCRIPTION OF THE DRAWINGS

The above object and features of the present
5 invention will be more apparent from the following
description given with reference to the accompanying
drawings, wherein:

Fig. 1 is a sectional view of an example of the
sectional structure of a reduced wind load overhead cable
10 of the related art;

Fig. 2 is a sectional view of other example of the
sectional structure of a reduced wind load overhead cable
of the related art;

Fig. 3 is a sectional view of an embodiment of an
15 overhead cable according to a first aspect of the present
invention;

Fig. 4 is a perspective view of the state of the
steel strands, the aluminum strands and the segment
strands twisted together;

20 Fig. 5 is an enlarged sectional view of a principal
part of the overhead cable shown in Fig. 3;

Fig. 6 is a sectional view of an embodiment of an
overhead cable according to a second aspect of the
present invention;

25 Fig. 7 is a graph of a drag coefficient

characteristic of an overhead cable of the present invention and an overhead cable of the related art according to the results of a wind tunnel experiment;

Fig. 8 is a graph of a drag coefficient
5 characteristic of an overhead cable of the present invention and an overhead cable of the related art according to the results of a wind tunnel experiment;

Fig. 9 is a graph of a drag coefficient
characteristic of an overhead cable of the present
10 invention and an overhead cable of the related art according to the results of a wind tunnel experiment;

Fig. 10 is a graph of a drag coefficient
characteristic of an overhead cable of the present
invention and an overhead cable of the related art
15 according to the results of a wind tunnel experiment; and

Fig. 11 is a graph of a drag coefficient
characteristic of an overhead cable of the present
invention and an overhead cable of the related art
according to the results of a wind tunnel experiment.

20

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Below, embodiments of the present invention will be explained by referring to the drawings.

Figure 3 is a sectional view of an embodiment of an
25 overhead cable according to the present invention.

This overhead cable is comprised of seven steel strands 1 serving as the tension-bearing core, 24 aluminum strands 2 serving as the conductive layer twisted around them, and a further 12 segment strands 3 5 having sector-form cross-sections serving as the outermost layer twisted around these strands.

In the outer circumferential surface area of each boundary of adjoining segment strands 3, a groove Tr extending along the longitudinal direction is formed.

10 Fig. 4 is a perspective view of the state of the steel strands, the aluminum strands and segment strands twisted together.

As seen from Fig. 4, the groove Tr is formed into a spiral-form.

15 In the outer circumferential contour of the cross-section of each of the 12 segment strands 3 having the sector-form cross-sections serving as the outermost layer, the contour of the groove Tr described above is comprised by an arc-shaped curve having a predetermined 20 radius R centered around a vertex Ap of a regular 12-sided polygon.

Further, the outer circumferential contour shape of each part between adjoining grooves Tr is comprised by an arc-shaped curve which is concave with respect to a 25 straight line connecting adjoining vertexes Ap of the

regular 12-sided polygon and intersects the arc-shaped curve having the predetermined radius R described above.

The diameter d of a circle Cir circumscribing the vertexes Ap of the regular 12-sided polygon is set to a value in a predetermined range in order to obtain the effect of reducing the wind load even at a relatively low design wind speed of about 40 m/s and is preferably set within the range from 12.8 to 42.6 mm.

Here, Fig. 5 is an enlarged sectional view of a principal part of the overhead cable shown in Fig. 3.

In Fig. 5, if the maximum depth of the arc-shaped curve which is concave with respect to the straight line connecting adjoining vertexes Ap of the regular 12-sided polygon from the related straight line is defined as D , this maximum depth D is set in a predetermined range with respect to the diameter d of the circle Cir circumscribing the vertexes Ap of the regular 12-sided polygon in order to obtain the effect of reducing the wind load. Preferably, the ratio D/d of the maximum depth D and the diameter d is within the range from 0.0 to 0.018.

In Fig. 5, if the maximum height from each vertex Ap of the regular 12-sided polygon to the bottom of the groove Tr is defined as H , this maximum height H is set to a value in a predetermined range with respect to the

diameter d of the circle Cir in order to obtain the effect of reducing the wind load. Preferably, the ratio H/d between the maximum height H and the diameter d is within a range from 0.0045 to 0.0357.

5 Also, the maximum height H from a vertex Ap to the bottom of the groove Tr is set to a value in a predetermined range with respect to the radius R of the groove Tr in order to obtain the effect of reducing the wind load. Preferably, the ratio H/R between the maximum
10 height H and the radius R is within the range from 0.08 to 1.0.

Further, in Fig. 3 and Fig. 5, the case where the number of the segment strands 3 constituting the outermost layer was set at 12 was shown, but in the
15 present invention, the number of the segment strands 3 is not limited to 12. Preferably, the number of the segment strands 3 is selected within a range from 12 to 24.

In the overhead cable according to the present embodiment having the above sectional structure, when the
20 wind strikes this overhead cable, the wind forms a thin boundary layer along the outer circumferential surface of the segment strands 3. This boundary layer is greatly agitated in the grooves Tr when passing through the grooves Tr and becomes turbulence. The breakaway point of
25 the boundary layer can be moved backward to the downwind

side of the segment strands 3 by the action of the grooves Tr making the flow turbulent and thus a wind load reducing effect is obtained.

In addition to the action of the grooves Tr, in the overhead cable according to the present embodiment, the basic contour shape of the segment strands 3 constituting the outermost layer is made not a circle, but a regular polygon, therefore the turbulence of the boundary layer is further promoted by the action of the shape of this regular polygon and the breakaway point of the boundary layer can be further moved backward on the downwind side of the segment strands 3 and therefore a further wind load reducing effect is obtained.

Further, in the overhead cable according to the present embodiment, a recess having a maximum depth D is formed in the outer circumferential surface of each segment strand 3 constituting the outermost layer, therefore a further wind load reducing effect is obtained by the action of the recesses on the boundary layer.

Figure 6 is a sectional view of other embodiment of an overhead cable according to the present invention.

Note that the same references are assigned to the same constituent parts as those of the overhead cable shown in Fig. 3.

The overhead cable shown in Fig. 6 is comprised of

seven steel strands 1 serving as the tension-bearing core, 24 aluminum strands 2 serving as the conductive layer twisted together around their outer circumference, and a further 12 segment strands 31 having fan-shaped cross-sections serving as the outermost layer twisted together at that outer circumference.

In the outer circumferential surface area of each boundary of adjoining segment strands 31, a spiral groove Tr extending along the longitudinal direction is formed.

10 In the outer circumferential contour of the cross-section of each of the 12 segment strands 31 having the fan-shaped cross-sections serving as the outermost layer, the contour of the groove Tr described above is comprised by an arc-shaped curve having a predetermined radius R

15 centered around a vertex Ap of a regular 12-sided polygon.

Further, the outer circumferential contour of each part between adjoining grooves Tr is comprised by a line segment located on a straight line connecting adjoining

20 vertexes Ap of the regular 12-sided polygon described above and intersecting the arc-shaped curves of the grooves Tr. Namely, the outer circumferential contour of the cross-sections of the 12 segment strands 31 having the sector-form cross-section serving as the outermost

25 layer are comprised by the sides of the regular 12-sided

polygon and the concave arc-shaped curves arranged at the vertexes.

The diameter d of the circle Cir circumscribing the vertexes Ap of the regular 12-sided polygon is set at a value in a predetermined range in order to obtain the effect of reducing the wind load even at the relatively low design wind speed of about 40 m/s. Preferably, it is set within a range from 12.8 mm to 42.6 mm.

Also, if the maximum height from each vertex Ap of the regular 12-sided polygon to the bottom of the groove Tr is defined as H , this maximum height H is set to a value in a predetermined range with respect to the diameter d of the circle Cir in order to obtain the effect of reducing the wind load. Preferably, the ratio H/d between the maximum height H and the diameter d is within the range from 0.0045 to 0.0357.

Further, the maximum height H from each vertex Ap to the bottom of the groove Tr is set to a value in the predetermined range with respect to the radius R of the groove Tr in order to obtain the effect of reducing the wind load. Preferably, the ratio H/R between the maximum height H and the radius R is within the range from 0.08 to 1.0.

Furthermore, in Fig. 6, the case where the number of the segment strands 31 constituting the outermost layer

was set at 12 was shown, but in the present invention, the number of the segment strands 31 is not limited to 12. Preferably, the number of the segment strands 31 is selected within the range from 12 to 24.

5 In the overhead cable according to the present embodiment, the point that a recess is not formed in the outer circumferential surface of each segment strand 31 is the point of difference from the overhead cable according to the first aspect of the present invention.

10 Accordingly, except for the action of the recess of the outer circumferential surface of each segment strand 31, a wind load reducing effect is obtained by a similar action to that of the overhead cable according to the first aspect of the present invention described above.

15 Figures 7 to 11 are graphs showing the results of wind tunnel experiments conducted to study the drag reduction characteristics for overhead cables having various structures, in which abscissas represent the wind speed (m/s) and the ordinates represent the drag
20 coefficient C_d . Note that the wind speed (m/s) was measured within a range from 10 m/s to 80 m/s since the highest wind speed used at the design of an ordinary overhead power transmission line is 40 m/s. Further, as
25 the overhead cable, use was made of the following steel-reinforced aluminum cables having diameters of 22 to 36.6

mm. The experiments were also conducted on conventional steel-reinforced aluminum cables (ACSR) for comparison (ones obtained by twisting together a plurality of strands having a circular cross-section).

5 1.810 mm² class

Cable 1 of present invention: $d = 36.6$ mm, 12
outermost layer segment strands, $D = 0.3$ mm, $R = 1.0$ mm,
 $H = 1.0$ mm.

10 Cable 2 of present invention: $d = 36.6$ mm, 12
outermost layer segment strands, $D = 0.3$ mm, $R = 2.0$ mm,
 $H = 0.3$ mm.

Cable 3 of present invention: $d = 36.6$ mm, 20
outermost layer segment strands, $D = 0.1$ mm, $R = 0.75$ mm,
 $H = 0.6$ mm.

15 Cable 4 of present invention: $d = 36.6$ mm, 20
outermost layer segment strands, $D = 0.1$ mm, $R = 1.5$ mm,
 $H = 0.75$ mm.

Cable 5 of related art (ACSR): $d = 38.4$ mm.

2.610 mm² class

20 Cable 6 of present invention: $d = 33$ mm, 16
outermost layer segment strands, $D = 0.15$ mm, $R = 0.9$ mm,
 $H = 0.9$ mm.

Cable 7 of present invention: $d = 33$ mm, 16
outermost layer segment strands, $D = 0.15$ mm, $R = 1.8$ mm,
25 $H = 0.26$ mm.

Cable 8 of related art (ACSR): $d = 34.2$ mm.

3.410 mm² class

Cable 9 of present invention: $d = 28$ mm, 14

outermost layer segment strands, $D = 0.15$ mm, $R = 0.75$
5 mm, $H = 0.75$ mm.

Cable 10 of present invention: $d = 28$ mm, 14

outermost layer segment strands, $D = 0.15$ mm, $R = 1.5$ mm,
 $H = 0.22$ mm.

Cable 11 of present invention: $d = 28$ mm, 24

10 outermost layer segment strands, $D = 0.05$ mm, $R = 1.25$
mm, $H = 1.0$ mm.

Cable 12 of present invention: $d = 28$ mm, 24

outermost layer segment strands, $D = 0.05$ mm, $R = 2.0$ mm,
 $H = 1.5$ mm.

15 Cable 13 of related art (ACSR): $d = 28.5$ mm.

4.240 mm² class

Cable 14 of present invention: $d = 22$ mm, 14

outermost layer segment strands, $D = 0.1$ mm, $R = 0.6$ mm,
 $H = 0.6$ mm.

20 Cable 15 of present invention: $d = 22$ mm, 14

outermost layer segment strands, $D = 0.1$ mm, $R = 0.9$ mm,
 $H = 0.26$ mm.

Cable 16 of present invention: $d = 22$ mm, 14

outermost layer segment strands, $D = 0.1$ mm, $R = 1.25$ mm,
25 $H = 0.1$ mm.

Cable 17 of present invention: $d = 22$ mm, 16
outermost layer segment strands, $D = 0.0$ mm, $R = 1.2$ mm,
 $H = 0.17$ mm.

Cable 18 of present invention: $d = 22$ mm, 16
5 outermost layer segment strands, $D = 0.1$ mm, $R = 1.2$ mm,
 $H = 0.17$ mm.

Cable 19 of present invention: $d = 22$ mm, 16
outermost layer segment strands, $D = 0.2$ mm, $R = 1.2$ mm,
 $H = 0.17$ mm.

10 Cable 20 of present invention: $d = 22$ mm, 16
outermost layer segment strands, $D = 0.4$ mm, $R = 1.2$ mm,
 $H = 0.17$ mm.

Cable 21 of related art (ACSR): $d = 22.4$ mm.

Figure 7 is a graph of the results of wind tunnel
15 experiments conducted to study the drag reduction
characteristics up to the wind speed 40 m/s for the cable
1 to the cable 5.

When investigating the drag coefficient C_d in Fig.
7, in the cable 5 of the related art, as represented by
20 the curve CV5, the drag coefficient C_d reaches a minimum
value around the wind speed 16 m/s. Thereafter, when the
wind speed becomes higher, the drag coefficient C_d is
somewhat increased. At the wind speed 40 m/s, the drag
coefficient C_d becomes almost 1.

25 On the other hand, in the cable 1 of the present

invention, as represented by the curve CV1, in the region lower than the wind speed of about 25 m/s, the drag coefficient C_d is higher than that of the cable 5 of the related art, but in the region exceeding the wind speed 25 m/s, the drag coefficient C_d is reduced from that of the cable 5 of the related art, and the drag coefficient C_d becomes about 0.9 or about 90% of that of the cable 5 of the related art.

Similarly, in the cable 2 of the present invention, as represented by the curve CV2, the coefficient becomes about 0.78 when the wind speed is 40 m/s or about 78% of that of the cable 5 of the related art. In the cable 3 of the present invention, as represented by the curve CV3, the coefficient becomes about 0.88 when the wind speed is 40 m/s or about 88% of that of the cable 5 of the related art. In the cable 4 of the present invention, as represented by the curve CV4, the drag coefficient C_d reaches a minimum value of about 0.65 when the wind speed is 25 to 30 m/s and becomes about 70% of that of the cable 5 of the related art when the wind speed is 40 m/s.

As seen from these results, when the cables 1 to 4 of the present invention are used, the design strength of the towers and other supports for overhead cables can be reduced and there is therefore a remarkable economical effect.

When comparing the cable 1 and cable 2 of the present invention and the cable 3 and cable 4, both of each have different design values of the maximum height H of the groove Tr and the radius R of the groove Tr . It is
5 seen that when these design values are different, a difference is created in the effect of reduction of the drag coefficient C_d . Namely, it is seen that the maximum height H and the radius R of the groove Tr are factors exerting an influence on the effect of reduction of the
10 drag coefficient C_d .

Further, as seen from the curve CV1 to the curve CV4, if the ratio H/R is large such as 1.0, the effect of reduction of the drag coefficient C_d is decreasing when the wind speed is within a range from 30 m/s to 40 m/s.
15 Also, as the drag coefficient is more reduced, the ratio H/R becomes smaller than 1.0.

Especially, when comparing the cable 2 and the cable 4, it is clearly seen the effect of reduction of the drag coefficient C_d at the wind speed within a range from 30
20 m/s to 40 m/s is obtained.

From these results, in a cable having a diameter of about 35 mm to 38 mm, it is seen that the effect of reduction of the drag coefficient is especially large if the ratio H/R is less than about 0.2 in case that the
25 number of the segment strands is 12 and the ratio H/R is

less than about 0.6 in case that the number of the segment strands is 20.

Figure 8 is a graph of the results of wind tunnel experiments conducted to study the drag reduction characteristics up to the wind speed 40 m/s for the cable 6 to the cable 8.

When investigating the drag coefficient C_d in Fig. 8, in the cable 8 of the related art, as represented by the curve CV8, the drag coefficient C_d reaches a minimum value around the wind speed 20 m/s. Thereafter, when the wind speed becomes higher, the drag coefficient C_d is somewhat increased. At the wind speed 40 m/s, the drag coefficient C_d becomes almost 0.95.

On the other hand, in the cable 6 and the cable 7 of the present invention, as represented by the graphs CV6 and CV7, it is seen that, in the region in which the wind speed exceeds 25 m/s, the drag coefficient C_d is lowered compared with the cable 8 of the related art in the two and the effect of reduction of the drag coefficient C_d is obtained.

Namely, even if the diameter d of the cable becomes small, i.e., 33 mm, in the region in which the wind speed exceeds 25 m/s, the effect of reduction of the drag coefficient C_d is obtained.

Further, when comparing the drag coefficients C_d of

the cable 6 and the cable 7, only the design values of the radius R and the maximum height H differ between the two, but it is seen that the characteristics of reduction of the drag coefficient C_d differ considerably according to these design values. Namely, it is seen that the wind speed zone in which the drag coefficient C_d is reduced varies according to these design values.

Further, when the wind speed is within a range from 30 m/s to 40 m/s, as seen from the graph CV6 and CV7, the larger effect of reduction of the drag coefficient C_d is obtained the value of H/R becomes smaller.

From this result, in a cable having a diameter of about 32 mm to 34 mm, it is seen that the effect of reduction of the drag coefficient C_d at the wind speed within a range from 30 m/s to 40 m/s is especially large if the ratio H/R is less than about 0.4 in case that the number of the segment strands is 16.

Figure 9 is a graph of the results of wind tunnel experiments conducted to study the drag reduction characteristics up to the wind speed 40 m/s for the cable 9 to the cable 13.

When investigating the drag coefficient C_d in Fig. 9, in the cable 13 of the related art, as represented by the curve CV13, the drag coefficient C_d reaches the minimum value around the wind speed 20 m/s. Thereafter,

the drag coefficient C_d is somewhat increased when the wind speed becomes higher. The drag coefficient C_d becomes almost 1 at the wind speed 40 m/s.

On the other hand, in the cable 9 to the cable 12 of the present invention, as represented by the graphs CV9 to CV12, it is seen that, in the region in which the wind speed exceeds 25 m/s, the effect of reduction of the drag coefficient C_d is obtained compared with the cable 13 of the related art.

At the wind speed with a range from 30 m/s to 40 m/s, as seen from the graph CV10, it is seen that the effect of reduction of the drag coefficient C_d in the cable 10 is especially large.

From this result, in a cable having a diameter of about 27 mm to 29 mm and 12 segment strands, it is seen that the effect of reduction of the drag coefficient C_d at the wind speed within a range from 30 m/s to 40 m/s is especially large if the ratio of H/R is less than about 0.2.

Figure 10 is a graph showing the results of wind tunnel experiments conducted to study the drag reduction characteristics up to the wind speed 80 m/s for the cable 14 to the cable 16 and the cable 21.

When investigating the drag coefficient C_d in Fig. 10, in the cable 21 of the related art, as represented by

the curve CV21, the drag coefficient C_d reaches the minimum value around the wind speed 25 m/s. Thereafter, the drag coefficient C_d is somewhat increased when the wind speed becomes higher. The drag coefficient C_d becomes almost 1 at the wind speed 70 m/s.

On the other hand, in the cable 14 of the present invention, it is seen that the effect of reduction of the drag coefficient C_d is obtained in the region exceeding the wind speed 30 m/s. In the cable 15 of the present invention, as represented by the curve CV15, it is seen that the effect of reduction of the drag coefficient C_d is obtained in the region exceeding the wind speed 35 m/s. In the cable 16 of the present invention, as represented by the curve CV16, it is seen that the effect of reduction of the drag coefficient C_d is obtained in the region exceeding the wind speed 40 m/s.

Namely, when comparing the cables 14 to 16 of the present invention, it is seen that the wind speed at which the effect of reduction of the drag coefficient C_d is obtained varies according to the change of H/R .

Also, when the diameter becomes relatively smaller, it is seen that the effect of reduction of the drag coefficient C_d at the speed within a range from 30 m/s to 40 m/s is larger the value of H/R becomes larger.

From the result, in a cable having a diameter of

about 21 mm to 23 mm and 14 segment strands is especially large if the ratio H/R is larger than about 0.5. Fig. 11 is a graph showing the results of wind tunnel experiments conducted to study the drag coefficient characteristics up to the wind speed 80 m/s for the cable 17 to the cable 21.

Note that the cable 17 of the present invention is a cable having no recess in the outer circumferential surface of the segment strands, while the cables 18 to 20 of the present invention are cables in which there is a recess in the outer circumferential surface of the segment strands. The other design values are the same.

When investigating the drag coefficient C_d in Fig. 11, in the cable 17 to the cable 20 of the present invention, as represented by the graphs CV17 to CV20, it is seen that there is a difference in the characteristic of reduction of the drag coefficient C_d according to the existence of the recess in the outer circumferential surface of the segment strands.

Namely, in the cable 17 of the present invention in which there is no recess in the outer circumferential surface of the segment strands, the effect of reduction of the drag coefficient C_d is obtained in the region exceeding the wind speed 50 m/s, but in the cable <18> to the cable 20 of the present invention in which the recess

exists in the outer circumferential surface of the segment strands, it is seen that the effect of reduction of the drag coefficient C_d is obtained even at a wind speed lower than the wind speed 50 m/s.

5 Further, it is also seen that the characteristic of reduction of the drag coefficient C_d varies according to the size of the maximum depth D of the recess in the outer circumferential surface of the segment strands.

10 The test results are shown arranged by the number of the segment strands in Table 1, arranged by H/d in Table 2, arranged by H/R in Table 3, and arranged by D/d in Table 4.

Table 1

Cable diameter d	Number of strands	Groove radius R	Groove height H	Depth D	20 m/s drag coefficient	30 m/s drag coefficient	40 m/s drag coefficient
36.6	12	1.00	1.00	0.30	1.039	0.913	0.918
36.6	12	2.00	0.30	0.30	1.036	0.791	0.773
22.0	14	0.60	0.60	0.10	1.158	0.823	0.778
22.0	14	0.90	0.26	0.10	1.216	0.965	0.739
22.0	14	1.25	0.10	0.10	1.23	1.172	0.838
28.0	14	0.75	0.75	0.15	0.995	0.776	0.818
28.0	14	1.50	0.22	0.15	1.129	0.787	0.724
22.0	16	1.20	0.17	0.00	1.242	1.201	0.811
22.0	16	1.20	0.17	0.10	1.24	1.123	0.782
22.0	16	1.20	0.17	0.20	1.235	1.082	0.751
22.0	16	1.20	0.17	0.40	1.214	0.945	0.835
33.0	16	0.90	0.90	0.15	0.791	0.791	0.802
33.0	16	1.80	0.26	0.15	1.113	0.604	0.623
36.6	20	0.75	0.60	0.10	0.929	0.853	0.878
36.6	20	1.50	0.75	0.10	0.803	0.651	0.713
28.0	24	1.25	1.00	0.05	0.815	0.816	0.818
28.0	24	2.00	1.50	0.05	0.919	0.923	0.923

11 12 13 14 15 16 17 18 19 20 21 22 23 24 25 26 27 28 29 30 31 32 33 34 35 36 37 38 39 40 41 42 43 44 45 46 47 48 49 50 51 52 53 54 55 56 57 58 59 60 61 62 63 64 65 66 67 68 69 70 71 72 73 74 75 76 77 78 79 80 81 82 83 84 85 86 87 88 89 90 91 92 93 94 95 96 97 98 99 100 101 102 103 104 105 106 107 108 109 110 111 112 113 114 115 116 117 118 119 120 121 122 123 124 125 126 127 128 129 130 131 132 133 134 135 136 137 138 139 140 141 142 143 144 145 146 147 148 149 150 151 152 153 154 155 156 157 158 159 160 161 162 163 164 165 166 167 168 169 170 171 172 173 174 175 176 177 178 179 180 181 182 183 184 185 186 187 188 189 190 191 192 193 194 195 196 197 198 199 200 201 202 203 204 205 206 207 208 209 210 211 212 213 214 215 216 217 218 219 220 221 222 223 224 225 226 227 228 229 230 231 232 233 234 235 236 237 238 239 240 241 242 243 244 245 246 247 248 249 250 251 252 253 254 255 256 257 258 259 260 261 262 263 264 265 266 267 268 269 270 271 272 273 274 275 276 277 278 279 280 281 282 283 284 285 286 287 288 289 290 291 292 293 294 295 296 297 298 299 300 301 302 303 304 305 306 307 308 309 310 311 312 313 314 315 316 317 318 319 320 321 322 323 324 325 326 327 328 329 330 331 332 333 334 335 336 337 338 339 340 341 342 343 344 345 346 347 348 349 350 351 352 353 354 355 356 357 358 359 360 361 362 363 364 365 366 367 368 369 370 371 372 373 374 375 376 377 378 379 380 381 382 383 384 385 386 387 388 389 390 391 392 393 394 395 396 397 398 399 400 401 402 403 404 405 406 407 408 409 410 411 412 413 414 415 416 417 418 419 420 421 422 423 424 425 426 427 428 429 430 431 432 433 434 435 436 437 438 439 440 441 442 443 444 445 446 447 448 449 450 451 452 453 454 455 456 457 458 459 460 461 462 463 464 465 466 467 468 469 470 471 472 473 474 475 476 477 478 479 480 481 482 483 484 485 486 487 488 489 490 491 492 493 494 495 496 497 498 499 500 501 502 503 504 505 506 507 508 509 510 511 512 513 514 515 516 517 518 519 520 521 522 523 524 525 526 527 528 529 530 531 532 533 534 535 536 537 538 539 540 541 542 543 544 545 546 547 548 549 550 551 552 553 554 555 556 557 558 559 560 561 562 563 564 565 566 567 568 569 570 571 572 573 574 575 576 577 578 579 580 581 582 583 584 585 586 587 588 589 590 591 592 593 594 595 596 597 598 599 600 601 602 603 604 605 606 607 608 609 610 611 612 613 614 615 616 617 618 619 620 621 622 623 624 625 626 627 628 629 630 631 632 633 634 635 636 637 638 639 640 641 642 643 644 645 646 647 648 649 650 651 652 653 654 655 656 657 658 659 660 661 662 663 664 665 666 667 668 669 670 671 672 673 674 675 676 677 678 679 680 681 682 683 684 685 686 687 688 689 690 691 692 693 694 695 696 697 698 699 700 701 702 703 704 705 706 707 708 709 710 711 712 713 714 715 716 717 718 719 720 721 722 723 724 725 726 727 728 729 730 731 732 733 734 735 736 737 738 739 740 741 742 743 744 745 746 747 748 749 750 751 752 753 754 755 756 757 758 759 760 761 762 763 764 765 766 767 768 769 770 771 772 773 774 775 776 777 778 779 780 781 782 783 784 785 786 787 788 789 790 791 792 793 794 795 796 797 798 799 800 801 802 803 804 805 806 807 808 809 810 811 812 813 814 815 816 817 818 819 820 821 822 823 824 825 826 827 828 829 830 831 832 833 834 835 836 837 838 839 840 841 842 843 844 845 846 847 848 849 850 851 852 853 854 855 856 857 858 859 860 861 862 863 864 865 866 867 868 869 870 871 872 873 874 875 876 877 878 879 880 881 882 883 884 885 886 887 888 889 890 891 892 893 894 895 896 897 898 899 900 901 902 903 904 905 906 907 908 909 910 911 912 913 914 915 916 917 918 919 920 921 922 923 924 925 926 927 928 929 930 931 932 933 934 935 936 937 938 939 940 941 942 943 944 945 946 947 948 949 950 951 952 953 954 955 956 957 958 959 960 961 962 963 964 965 966 967 968 969 970 971 972 973 974 975 976 977 978 979 980 981 982 983 984 985 986 987 988 989 990 991 992 993 994 995 996 997 998 999 1000

Table 2

Cable diameter d	Number of strands	Groove radius R	Groove height H	Depth D	H/d	20 m/s drag coefficient	30 m/s drag coefficient	40 m/s drag coefficient
22.0	14	1.25	0.10	0.10	0.0045	1.23	1.172	0.838
22.0	16	1.20	0.17	0.00	0.0077	1.242	1.201	0.811
22.0	16	1.20	0.17	0.10	0.0077	1.24	1.123	0.782
22.0	16	1.20	0.17	0.20	0.0077	1.235	1.082	0.751
22.0	16	1.20	0.17	0.40	0.0077	1.214	0.945	0.835
28.0	14	1.50	0.22	0.15	0.0079	1.129	0.787	0.724
33.0	16	1.80	0.26	0.15	0.0079	1.113	0.604	0.623
36.6	12	2.00	0.30	0.30	0.0082	1.036	0.791	0.773
22.0	14	0.90	0.26	0.10	0.0118	1.216	0.965	0.739
36.6	20	0.75	0.60	0.10	0.0164	0.929	0.853	0.878
36.6	20	1.50	0.75	0.10	0.0205	0.803	0.651	0.713
28.0	14	0.75	0.75	0.15	0.0268	0.995	0.776	0.818
22.0	14	0.60	0.60	0.10	0.0273	1.158	0.823	0.778
33.0	16	0.90	0.90	0.15	0.0273	0.791	0.791	0.802
36.6	12	1.00	1.00	0.30	0.0273	1.039	0.913	0.918
28.0	24	1.25	1.00	0.05	0.0357	0.815	0.816	0.818
28.0	24	2.00	1.50	0.05	0.0536	0.919	0.923	0.923

Table 3

Cable diameter d	Number of strands	Groove radius R	Groove height H	Depth D	H/R	20 m/s drag coefficient	30 m/s drag coefficient	40 m/s drag coefficient
22.0	14	1.25	0.10	0.10	0.0800	1.23	1.172	0.838
22.0	16	1.20	0.00	0.00	0.1417	1.242	1.201	0.811
22.0	16	1.20	0.10	0.10	0.1417	1.24	1.123	0.782
22.0	16	1.20	0.20	0.20	0.1417	1.235	1.082	0.751
22.0	16	1.20	0.40	0.40	0.1417	1.214	0.945	0.835
33.0	16	1.80	0.15	0.15	0.1444	1.113	0.604	0.623
28.0	14	1.50	0.15	0.15	0.1467	1.129	0.787	0.724
36.6	12	2.00	0.30	0.30	0.1500	1.036	0.791	0.773
22.0	14	0.90	0.10	0.10	0.2889	1.216	0.965	0.739
36.6	20	1.50	0.10	0.10	0.5000	0.803	0.651	0.713
28.0	24	2.00	0.05	0.05	0.7500	0.919	0.923	0.923
36.6	20	0.75	0.10	0.10	0.8000	0.929	0.853	0.878
28.0	14	1.25	0.05	0.05	0.8000	0.815	0.816	0.818
22.0	14	0.60	0.10	0.10	1.0000	1.158	0.823	0.778
28.0	14	0.75	0.15	0.15	1.0000	0.995	0.776	0.818
33.0	16	0.90	0.15	0.15	1.0000	0.791	0.791	0.802
36.6	12	1.00	0.30	0.30	1.0000	1.039	0.913	0.918

Table 4

Cable diameter d	Number of strands	Groove radius R	Groove height H	Depth D	D/d	20 m/s drag coefficient	30 m/s drag coefficient	40 m/s drag coefficient
22.0	16	1.20	0.17	0.00	0.0000	1.242	1.201	0.811
28.0	24	1.25	1.00	0.05	0.0018	0.815	0.816	0.818
28.0	24	2.00	1.50	0.05	0.0018	0.919	0.923	0.923
36.6	20	0.75	0.60	0.10	0.0027	0.929	0.853	0.878
36.6	20	1.50	0.75	0.10	0.0027	0.803	0.651	0.713
33.0	16	0.90	0.90	0.15	0.0045	0.791	0.791	0.802
33.0	16	1.80	0.26	0.15	0.0045	1.113	0.604	0.623
22.0	14	1.25	0.10	0.10	0.0045	1.23	1.172	0.838
22.0	14	0.60	0.60	0.10	0.0045	1.158	0.823	0.778
22.0	14	0.90	0.26	0.10	0.0045	1.216	0.965	0.739
22.0	16	1.20	0.17	0.10	0.0045	1.24	1.123	0.782
28.0	14	0.75	0.75	0.15	0.0054	0.995	0.776	0.818
28.0	14	1.50	0.22	0.15	0.0054	1.129	0.787	0.724
36.6	12	1.00	1.00	0.30	0.0082	1.039	0.913	0.918
26.6	12	2.00	0.30	0.30	0.0082	1.036	0.791	0.773
22.0	16	1.20	0.17	0.20	0.0091	1.235	1.082	0.751
22.0	16	1.20	0.17	0.40	0.0182	1.214	0.945	0.835

Table 1 shows the relationship between the number of the segment strands and the effect of reduction of the drag coefficient. According to Table 1, at the wind speed 40 m/s, it is seen that the effect of reduction of the drag coefficient, that is, the reduction of the wind load, is obtained within a range from a regular 12-sided polygon to a regular 24-sided polygon (preferably within a range from a regular 14-sided polygon to a regular 20-sided polygon).

Table 2 shows the relationship between the H/d and the effect of reduction of the drag coefficient. According to Table 2, it is seen that, at the wind speed 40 m/s, the effect of reduction of the wind load is obtained when H/d is within the range from 0.0045 to 0.0357 (preferably within a range from 0.0077 to 0.0205).

Table 3 shows the relationship between the H/R and the effect of reduction of the drag coefficient. According to Table 3, it is seen that, at the wind speed 40 m/s, the effect of reduction of the wind load is obtained when H/R is within the range from 0.08 to 1.0 (preferably within a range from 0.14 to 0.50).

Table 4 shows the relationship between the D/d and the effect of reduction of the drag coefficient. According to Table 4, it is seen that, at the wind speed 40 m/s, the effect of reduction of the wind load is

obtained when D/d is within a range not more than 0.0182
(preferably in a range not more than 0.0091).

Particularly in a cable having a diameter of 22 mm, it is
seen that, if D/d becomes 0.0045 or less, a large wind
5 load reduction effect is created in the design wind speed
zone.

The above experiments were carried out for cables
having the diameters of 22 to 36.6 mm.

According to the results of experiments shown in
10 Fig. 7 to Fig. 11, it is clear that, in the case of the
design wind speed 40 m/s of a general overhead cable, the
effect of the reduction of the wind load is obtained
within the range of diameters described above.

Further, when the ranges of the thickness of the
15 cables in which the effect of the present invention is
obtained are sought by using the Reynolds number $Re =$
 Ud/v (U : wind speed, d : outer diameter of the cable, v :
standard atmospheric state or 1.473×10^{-5}), the
following ranges are obtained.

20 According to the results of the experiments shown in
Fig. 11, it is apparent that the effect of reduction of
the wind speed is obtained where the wind speed is within
a range from 35 to 77.5 m/s in the cable 17 to the cable
20 of the present invention having the diameter of 22 mm.

25 By this, when seeking the minimum outer diameter d_1

and the maximum outer diameter d2 of the cables exhibiting the wind load reduction effect by using the Reynolds number Re, they are as follows.

Case where the design wind speed is 40 m/s

5 $Re = 35 \times 22/v = 40 \times d1/v$, accordingly $d1 = 19.3$ mm

$Re = 77.5 \times 22/v = 40 \times d2/v$, accordingly $d2 = 42.6$
mm

Case where the design wind speed is 50 m/s

10 (mountainous district etc.)

$Re = 35 \times 22/v = 50 \times d1/v$, accordingly $d1 = 15.4$ mm

$Re = 77.5 \times 22/v = 50 \times d2/v$, accordingly $d2 = 34.1$
mm

15 Case where the design wind speed is 60 m/s (isle
such as Okinawa etc.)

$Re = 35 \times 22/v = 60 \times d1/v$, accordingly $d1 = 12.8$ mm

$Re = 77.5 \times 22/v = 60 \times d2/v$, accordingly $d2 = 28.4$
mm

20 Accordingly, in the cables of the present invention,
though depending on the design wind speed, it is possible
to reduce the wind load within a range of diameters from
12.8 to 42.6 mm, preferably within a range from 15.4 to
42.6 mm.

25 The overhead cables according to the embodiments
were steel-reinforced aluminum cables, but the overhead

cable of the present invention relates to the sectional shape of the cables, so it can be similarly applied to also copper cable, overhead ground wires, and covered cables.

5 Further, similar effects are obtained even if using, instead of the tension-bearing steel core of the cable, superior temperature elongation characteristic Invar wire, silicon carbide filaments, carbon fiber, alumina fiber, or aramide fiber plated or coated on the surface
10 with aluminum, zinc, chromium, copper, or the like.

 As explained above, according to the present invention, by making the sectional shape of the cable a regular polygon and arranging arc-shaped grooves in the vertex portions, the reduction of the wind load of a
15 small sized cable, which was never achieved in the related art, becomes possible.

 Further, according to the present invention, the outermost layer can be constituted by a single type of segment strand having a simple shape, therefore a wind
20 load cable can be provided at low cost without a special manufacturing technique or an increase of costs.